

Seac Ltd

Unit 2-4 Chartwell Drive
Leicester
Leicestershire LE18 2FL

Tel: 0116 2887719 Fax: 0116 257 2069

e-mail: sales@seac.co.uk

website: www.seac.co.uk



Agrément Certificate

19/5608

Product Sheet 2

WRAPTOR BREATHABLE MEMBRANES

FOR USE IN COLD NON-VENTILATED ROOFS

This Agrément Certificate Product Sheet⁽¹⁾ relates to WRAPTOR Breathable Membranes, flexible three-layer polypropylene sheet materials for use as roof tile underlays in cold non-ventilated pitched roof systems.

(1) Hereinafter referred to as 'Certificate'.

CERTIFICATION INCLUDES:

- factors relating to compliance with Building Regulations where applicable
- factors relating to additional non-regulatory information where applicable
- independently verified technical specification
- assessment criteria and technical investigations
- design considerations
- installation guidance
- regular surveillance of production
- formal three-yearly review.

KEY FACTORS ASSESSED

Weathertightness — as part of a complete roof, the products will resist the passage of water and wind-blown snow and dust into the interior of a building (see section 6).

Condensation — the products are low water vapour resistance (Type LR) membranes and can be used as part of cold non-ventilated pitched roof systems (see section 7).

Wind loading — when installed on appropriately spaced battens and/or rafters, the products' physical properties are adequate to resist the wind loads imposed on the underlay. The products will reduce the wind uplift forces acting on the roof covering (see section 8).

Strength — the products have adequate strength to resist the loads associated with installation of the roof (see section 9).

Properties in relation to fire — the products are classified as Class E in accordance with BS EN 13501-1 : 2007 and their use is restricted in some cases by the national Building Regulations (see section 10).

Durability — under the normal conditions found in a roof space, the products will have a service life comparable to traditional roof tile underlays (see section 12).


The BBA has awarded this Certificate to the company named above for the products described herein. The products have been assessed by the BBA as being fit for their intended use provided they are installed, used and maintained as set out in this Certificate.

On behalf of the British Board of Agrément

Date of Second issue: 13 July 2022

Originally certificated on 26 February 2019

Hardy Giesler
Chief Executive Officer



The BBA is a UKAS accredited certification body – Number 113.

*The schedule of the current scope of accreditation for product certification is available in pdf format via the UKAS link on the BBA website at www.bbacerts.co.uk
Readers MUST check the validity and latest issue number of this Agrément Certificate by either referring to the BBA website or contacting the BBA directly.*

Any photographs are for illustrative purposes only, do not constitute advice and should not be relied upon.

British Board of Agrément

Bucknalls Lane
Watford
Herts WD25 9BA

©2022

Page 1 of 10

tel: 01923 665300
clientservices@bbacerts.co.uk
www.bbacerts.co.uk

Regulations

In the opinion of the BBA, WRAPTOR Breathable Membranes for use in cold non-ventilated roofs, if installed, used and maintained in accordance with this Certificate, can satisfy or contribute to satisfying the relevant requirements of the following Building Regulations (the presence of a UK map indicates that the subject is related to the Building Regulations in the region or regions of the UK depicted):



The Building Regulations 2010 (England and Wales) (as amended)

| | | |
|---------------------------------|--------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Requirement: Comment: | B3(4) | Internal fire spread The products are restricted by this Requirement. See section 10.1 of this Certificate. |
| Requirement: Comment: | B4(1) | External fire spread The products are restricted by this Requirement, in some circumstances. See sections 10.1 and 10.2 of this Certificate. |
| Requirement: Comment: | C2(b) | Resistance to moisture The products will contribute to a roof satisfying this Requirement. See section 6.1 of this Certificate. |
| Requirement: Comment: | C2(c) | Resistance to moisture The products will enable a roof to satisfy this Requirement with regard to interstitial condensation. See section 7 of this Certificate. |
| Regulation: Comment: | 7(1) | Materials and workmanship The products are acceptable materials. See section 12 and the <i>Installation</i> part of this Certificate. |



The Building (Scotland) Regulations 2004 (as amended)

| | | |
|---------------------------------------------|-----------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Regulation: Comment: | 8(1) | Durability, workmanship and fitness of materials The products can contribute to a roof satisfying this Regulation. See section 12 and the <i>Installation</i> part of this Certificate. |
| Regulation: Standard: Comment: | 9 2.4 | Building standards applicable to construction Cavities Consideration needs to be taken of the need for cavity barriers in association with the products to satisfy this Standard with respect to clause 2.4.2 ⁽¹⁾⁽²⁾ . See section 10.1 of this Certificate. |
| Standard: Comment: | 2.6 | Spread to neighbouring buildings The products are restricted under clause 2.6.4 ⁽¹⁾⁽²⁾ of this Standard, in some circumstances. See sections 10.1 and 10.3 of this Certificate. |
| Standard: Comment: | 2.7 | Spread on external walls The products are restricted under clause 2.7.1 ⁽¹⁾⁽²⁾ . See sections 10.1 and 10.3 of this Certificate. |
| Standard: Comment: | 3.10 | Precipitation The products will contribute to a roof satisfying clauses 3.10.1 ⁽¹⁾⁽²⁾ and 3.10.8 ⁽¹⁾⁽²⁾ of this Standard. See section 6.1 of this Certificate. |
| Standard: Comment: | 3.15 | Condensation The products can enable a roof to satisfy this Standard with regard to interstitial condensation, with reference to clauses 3.15.1 ⁽¹⁾⁽²⁾ , 3.15.3 ⁽¹⁾⁽²⁾ and 3.15.7 ⁽¹⁾⁽²⁾ . See section 7 of this Certificate. |

Standard: 7.1(a) **Statement of sustainability**
Comment: The products can contribute to meeting the relevant requirements of Regulation 9, Standards 1 to 6 and therefore will contribute to a construction meeting a bronze level of sustainability as defined in this Standard.

Regulation: 12 **Building standards applicable to conversions**
Comment: Comments given for the products under Regulation 9, Standards 1 to 6 also apply to this Regulation, with reference to clause 0.12.1⁽¹⁾⁽²⁾ and Schedule 6⁽¹⁾⁽²⁾.

(1) Technical Handbook (Domestic).
(2) Technical Handbook (Non-Domestic).



The Building Regulations (Northern Ireland) 2012 (as amended)

Regulation: 23(a)(i) **Fitness of materials and workmanship**
Comment: (iii)(b)(i) The products are acceptable. See section 12 and the *Installation* part of this Certificate.

Regulation: 28(b) **Resistance to moisture and weather**
Comment: The products will contribute to a roof satisfying this Regulation. See section 6.1 of this Certificate.

Regulation: 29 **Condensation**
Comment: The products will contribute to a roof to satisfy this Regulation. See section 7 of this Certificate.

Regulation: 35(4) **Internal fire spread - structure**
Comment: The products are restricted by this Regulation. See section 10.1 of this Certificate.

Construction (Design and Management) Regulations 2015

Construction (Design and Management) Regulations (Northern Ireland) 2016

Information in this Certificate may assist the client, designer (including Principal Designer) and contractor (including Principal Contractor) to address their obligations under these Regulations.

See sections: 1 *Description* (1.1), 10 *Properties in relation to fire* (10.4) and 14 *General* (14.3) of this Certificate.

Additional Information

CE marking

The Certificate holder has taken the responsibility of CE marking the products in accordance with harmonised European Standard BS EN 13859-1 : 2014.

Technical Specification

1 Description

1.1 WRAPTOR Breathable Membranes for use in cold non-ventilated roofs are three-layer polypropylene laminate composites with the nominal characteristics given in Table 1.

Table 1 Nominal characteristics

| Characteristic (unit) | WRAPTOR | | |
|--------------------------------------------------------------------------------------------------------|----------|----------|----------|
| | 100 | 120 | 140 |
| Thickness (mm) | 0.35 | 0.43 | 0.48 |
| Mass per unit area (g·m ⁻²) | 100 | 120 | 140 |
| Roll length (m) | 50 | 50 | 50 |
| Roll width (m) | 1 or 1.5 | 1 or 1.5 | 1 or 1.5 |
| Colour | | | |
| upper | grey | brown | blue |
| lower | white | white | blue |
| Tensile strength (N per 50 mm) | | | |
| longitudinal | 150 | 180 | 200 |
| transverse | 100 | 120 | 150 |
| Elongation (%) | | | |
| longitudinal | ≥50 | ≥50 | ≥50 |
| transverse | ≥50 | ≥50 | ≥50 |
| Tear resistance (N) | | | |
| longitudinal | 70 | 95 | 105 |
| transverse | 80 | 115 | 120 |
| Resistance to air penetration [m ³ ·m ⁻² ·h ⁻¹ @50 Pa ⁻¹] | 0.093 | — | — |
| Watertightness | | | |
| unaged | W1 | W1 | W1 |
| aged ⁽²⁾ | W1 | W1 | W1 |
| Equivalent air layer thickness (s _d) (m) | 0.02 | 0.05 | 0.02 |

(1) Aged in accordance with BS EN 13859-1 : 2014, Annex C.

1.2 The Certificate holder can provide details of a suitable tape for taping the overlaps.

2 Manufacture

2.1 The membranes are manufactured by a thermal-bonding process in which a polyethylene breathable film is bonded together with two layers of non-woven membranes to form a flexible vapour permeable roof tile underlay.

2.2 As part of the assessment and ongoing surveillance of product quality, the BBA has:

- agreed with the manufacturer the quality control procedures and product testing to be undertaken
- assessed and agreed the quality control operated over batches of incoming materials
- monitored the production process and verified that it is in accordance with the documented process
- evaluated the process for management of nonconformities
- checked that equipment has been properly tested and calibrated
- undertaken to carry out the above measures on a regular basis through a surveillance process, to verify that the specifications and quality control being operated by the manufacturer are being maintained.

3 Delivery and site handling

3.1 Rolls are delivered to site, individually wrapped in polythene that carries a label bearing the BBA logo incorporating the number of this Certificate.

3.2 The rolls should be stored flat or on end, on a clean, level surface, under cover and protected from sunlight.

Assessment and Technical Investigations

The following is a summary of the assessment and technical investigations carried out on WRAPTOR Breathable Membranes for use in cold non-ventilated roofs.

4 Use

4.1 WRAPTOR Breathable Membranes for use in cold non-ventilated roofs are satisfactory for use in dwellings with non-ventilated tiled or slated roofs of any conventional plan and size. Features⁽¹⁾ assessed include:

- duo pitched
- gable ends
- room-in-roof⁽²⁾
- mono-pitched
- verges
- dormers
- hipped
- abutments
- timber sarking⁽³⁾⁽⁴⁾⁽⁵⁾
- mansard
- valleys.

- (1) For roofs incorporating other features, non-conventional roof geometries or construction materials, the advice of the Certificate holder should be sought.
- (2) Where a room-in-roof results in part of a roof pitch being insulated (ie a warm roof), design and detailing of that part of the roof should comply with the relevant guidance given in Product Sheet 1 of this Certificate.
- (3) Timber sarking, Scottish practice: the membrane is laid over open jointed timber planks (nominally 150 mm wide with a 2 mm gap) and fixed with galvanized clout nails. Slates are nailed through the membrane on the sarking without battens.
- (4) Timber sarking planks, tiled roofs: counterbattens of 12 mm minimum thickness should be used to provide a drainage path beneath the tiling battens. The membrane may be laid directly over the timber planks or draped over the counterbattens.
- (5) Sheet sarking materials should not be used.

4.2 It is important that the designers, planners, contractors and/or installers ensure that the roof and ceiling are constructed in accordance with the Certificate holder's instructions and the information given in this Certificate.

4.3 The products can be installed by draping over rafters and securing with tiling battens, or installed taut over rafters and secured with counterbattens and tiling battens.

4.4 In conventionally ventilated roof constructions, energy loss by ventilation can account for up to 25% of the total heat lost through the roof. The non-ventilated roof system will significantly reduce this mechanism of heat loss.

4.5 In non-ventilated roof systems, the risk of condensation is equivalent to, or less than, that for conventionally ventilated cold roof systems (see section 7).

5 Practicability of installation

The products are designed to be installed by competent slaters/tilers, experienced with these types of products.

6 Weathertightness



6.1 The products are classified as Class W1 in accordance with BS EN 13859-1 : 2014 and will resist the passage of water, wind-blown snow and dust into the interior of a building under all conditions to be found in a roof constructed in accordance with the relevant clauses of BS 5534 : 2014.

6.2 The products resist the penetration of liquid water and consequently may be used as temporary waterproofing prior to the installation of slates or tiles. The period of such use should, however, be kept to a minimum. Further information is given in BBA Information Bulletin No 2 *Permeable Roof Tile Underlay — Guide to Good Site Practice*.

7 Condensation



7.1 For design purposes, the products' water vapour resistance may be taken as not more than $0.25 \text{ MN}\cdot\text{s}\cdot\text{g}^{-1}$, and for roofs designed in accordance with BS 5534 : 2014 or BS 5250 : 2021, they may be regarded as Type LR membranes.

7.2 The complete roof construction, ceiling boards to roof tiles, must be considered as a total system with regard to condensation risk. It is important that the products are laid in accordance with the Certificate holder's instructions and this Certificate, to minimise the risk of condensation.

7.3 The risk of condensation is highest in new-build construction during the first heating period, where there is high moisture loading owing to wet trades, such as in-situ cast concrete slabs or plaster. The risk of condensation diminishes as the building naturally dries out. See BBA Information Bulletin No 1 *Roof Tile Underlays in Cold Roofs during the Drying-out Period*.

7.4 All penetrations into and out of the roof space must be properly sealed in accordance with the Certificate holder's instructions, which include the use of the Certificate holder's recommended sealing tape. In addition, such features as vent stacks and boiler flues passing through the roof space must be sealed.

7.5 It is essential to minimise water vapour transfer into the loft space from the dwelling below. Appropriate measures include:

- ventilating the dwelling below, in accordance with the national Building Regulations and Standards for the dispersal and rapid dilution of water vapour, particularly from rooms that may experience high humidity (such as kitchens, utility rooms and bathrooms)
- covering all water tanks in the loft space and lagging pipework
- sealing penetrations in the ceiling and making loft hatches convection-tight by using a compressible draught seal
- ensuring that there is continuity of jointing with walls (and behind wall linings) at ceiling perimeters
- ensuring that masonry wall cavities do not interconnect with roof cavities.

7.6 For additional protection, the use of a vapour control layer/vapour check plasterboard can be considered.

8 Wind loading

8.1 Project design wind speeds for the roof in which the products are installed should be determined and wind uplift forces calculated, by a suitably experienced and competent individual in accordance with BS EN 1991-1-4 : 2005 and its UK National Annex.

Unsupported

8.2 The products are satisfactory for use in unsupported systems in the geographical Wind Zones given in Table 2, where a well-sealed ceiling as defined in BS 9250 : 2007, Clause 3.7, is present and the roof has a ridge height of ≤ 15 m, a pitch between 12.5 and 75°, and a site altitude of ≤ 100 m, and where topography is not significant. For all other cases, the required uplift resistance should be determined using BS 5534 : 2014 and the Certificate holder's declared wind uplift resistances given in Table 3.

Table 2 Zones of applicability of WRAPTOR Breathable Membranes according to BS 5534 : 2014, clause A.8 with battened laps and taped laps

| Product | ≤ 345 mm batten gauge with battened laps | ≤ 250 mm batten gauge with battened laps | ≤ 345 mm batten gauge with taped laps | ≤ 250 mm batten gauge with taped laps |
|-------------|-----------------------------------------------|-----------------------------------------------|--------------------------------------------|--------------------------------------------|
| WRAPTOR 100 | unclassified | Zones 1 to 2 | Zones 1 to 2 | Zones 1 to 5 |
| WRAPTOR 120 | unclassified | Zones 1 to 3 | Zones 1 to 3 | Zones 1 to 5 |
| WRAPTOR 140 | unclassified | Zones 1 to 3 | Zones 1 to 4 | Zones 1 to 5 |

Table 3 Declared wind uplift resistance (Pa)

| Product | ≤ 345 mm batten gauge with battened laps ⁽¹⁾ | ≤ 250 mm batten gauge with battened laps ⁽¹⁾⁽²⁾ | ≤ 345 mm batten gauge with taped laps ⁽¹⁾ | ≤ 250 mm batten gauge with taped laps ⁽¹⁾⁽²⁾ |
|-------------|--------------------------------------------------------------|-----------------------------------------------------------------|-----------------------------------------------------------|--------------------------------------------------------------|
| WRAPTOR 100 | 409 | 1080 | 985 | 2177 |
| WRAPTOR 120 | 466 | 1166 | 1313 | 2263 |
| WRAPTOR 140 | 529 | 1301 | 1482 | 2651 |

(1) Mean of test results.

(2) Underlays with a wind uplift resistance at a 250 mm batten gauge that satisfy the minimum design wind pressure of 820 Pa for Zone 1 are deemed to satisfy the requirements for use at 100 mm batten gauge in all Wind Zones.

Supported

8.3 Timber sarking, such as square-edged butt jointed planks, are not considered to be airtight and the underlay is treated as unsupported.

9 Strength

The products will resist the normal loads associated with installation of the roof.

10 Properties in relation to fire



10.1 The products are classified as Class E⁽¹⁾ in accordance with BS EN 13501-1 : 2007.

(1) Report reference PB 5.1/08-004/3, conducted by MFPA Leipzig GmbH. Report is available from the Certificate holder upon request.



10.2 In England and Wales, the products, when used in pitches of greater than 70°, should not be used on buildings that have a storey at least 18 m above ground level and which contain: one or more dwellings, an institution, a room for residential purposes (excluding any room in a hostel, hotel or boarding house), student accommodation, care homes, sheltered housing, hospitals or dormitories in boarding schools.



10.3 In Scotland, the products, when used in pitches greater than 70°, excluding upstands, should not be used on domestic or shared residential buildings in Scotland that have a storey more than 18 m above ground level.

10.4 When the products are used unsupported, there is a risk that fire can spread if the materials are accidentally ignited during maintenance works, eg by a roofer's or plumber's torch. As with all types of underlay, care should be taken during building and maintenance to avoid material being ignited.

10.5 When the products are used with timber sarking, such as square-edged butt jointed planks, the reaction to fire will be primarily determined by the sarking.

11 Maintenance

As the products are confined within the roof system and have suitable durability (see section 12), maintenance is not required. However, any damage occurring before enclosure must be repaired (see section 17).

12 Durability



The products will be virtually unaffected by the normal conditions found in a roof space and will have a life comparable to that of traditional roof tile underlays, provided they are not exposed to sunlight for long periods (see section 14.5). Advice regarding exposure can be obtained from the Certificate holder.

13 Reuse and recyclability

The products contain polypropylene, which can be recycled.

Installation

14 General

14.1 WRAPTOR Breathable Membranes for use in cold non-ventilated roofs must be installed and fixed in accordance with the Certificate holder's instructions, the provisions of this Certificate and the relevant recommendations of BS 5534 : 2014, BS 8000-0 : 2014 and BS 8000-6 : 2013. Installation can be carried out under all conditions normal to roofing work.

14.2 The products are installed with the coloured or printed side uppermost and lapped to shed water out and down the slope.

14.3 The products have a high coefficient of friction, either wet or dry, giving a slip-resistant surface for increased safety during the installation of the tiles and slates.

14.4 Overlaps must be provided with the minimum dimensions given in Table 4. The Certificate holder's advice must be sought when using tapes for sealing overlaps.

Table 4 Minimum overlaps

| Roof pitch (°) | Horizontal laps (mm) untaped and taped | | Vertical laps (mm) |
|----------------|----------------------------------------|-----------------|--------------------|
| | Not fully supported | Fully supported | |
| 12.5 < 15 | 225 | 150 | 100 |
| ≥15 | 150 | 100 | 100 |

14.5 Where possible, eaves guards should be used to protect the products from sunlight and direct water into the gutter.

15 Procedure

Draped and loose laps

15.1 The products should be installed as an unsupported system and fixed in the traditional method for roof tile underlays, ie draped between the rafters, with the coloured/printed side uppermost.

Taut

15.2 The products should be laid horizontally and must be pulled taut and not allowed to drape. Each sheet should be fixed to hold it in position prior to the counterbattens being fixed. Counterbattens (minimum thickness 12 mm) are then fixed to the rafter.

Timber plank sarking

15.3 For fully supported roofs (traditional Scottish), the slates can be nailed through the products into the timber plank sarking, normally 150 mm wide with a 2 mm gap. The underlay must be fixed to the sarking using galvanized clout nails.

15.4 For fully supported roofs (where battens are used), counterbattens of a minimum thickness of 12 mm should be installed either above or beneath the underlay, for drainage purposes.

16 Finishing

16.1 Detailing of abutments, verges and hips must be in accordance with the Certificate holder's instructions.

16.2 To minimise the risk of condensation, it is important that the details stated in sections 7.3, 7.5 and 7.6 are maintained.

16.3 Tiling and slating must be carried out in accordance with the relevant clauses of BS 5534 : 2014, BS 8000-0 : 2014, BS 8000-6 : 2013 and the tile/slate manufacturer's instructions, especially when using tightly jointed slates or tiles, where a ventilated batten space should be provided.

17 Repair

Damage to the products can be repaired prior to the installation of slates or tiles by patching and sealing the damaged areas. Care must be taken to ensure that the watertightness of the roof is maintained.

18 Tests

18.1 An assessment was made of data in relation to:

- dimensions
- mass per unit area
- tensile strength and elongation
- resistance to tear
- dimensional stability
- resistance to water penetration
- resistance to artificial ageing
- water vapour transmission
- resistance to air penetration
- reaction to fire.

18.2 Tests were carried out to determine:

- slip resistance
- resistance to streaming water
- Mullen burst strength
- resistance to wind loads

in order to assess:

- safety during installation
- performance under typical service conditions
- robustness during installation
- properties when installed.

19 Investigations

19.1 The manufacturing process was evaluated, including the methods adopted for quality control, and details were obtained of the quality and composition of the materials used.

19.2 Using computer modelling, cold non-ventilated roofs were analysed for risk of condensation.

Bibliography

BS 5250 : 2021 *Management of moisture in buildings – Code of practice*

BS 5534 : 2014 + A2 : 2018 *Slating and tiling for pitched roofs and vertical cladding — Code of practice*

BS 8000-0 : 2014 *Workmanship on construction sites – Introduction and general principles*

BS 8000-6 : 2013 *Workmanship on building sites — Code of practice for slating and tiling of roofs and claddings*

BS 9250 : 2007 *Code of practice for design of the airtightness of ceilings in pitched roofs.*

BS EN 1991-1-4 : 2005 + A1 : 2010 *Eurocode 1 : Actions on structures — General actions — Wind actions*

NA to BS EN 1991-1-4 : 2005 + A1 : 2010 UK National Annex to *Eurocode 1 : Actions on structures — General actions — Wind actions*

BS EN 13501-1 : 2007 + A1 : 2009 *Fire classification of construction products and building elements — Classification using test data from reaction to fire tests*

BS EN 13859-1 : 2014 *Flexible sheets for waterproofing — Definitions and characteristics of underlays — Underlays for discontinuous roofing*

20 Conditions

20.1 This Certificate:

- relates only to the product/system that is named and described on the front page
- is issued only to the company, firm, organisation or person named on the front page – no other company, firm, organisation or person may hold or claim that this Certificate has been issued to them
- is valid only within the UK
- has to be read, considered and used as a whole document – it may be misleading and will be incomplete to be selective
- is copyright of the BBA
- is subject to English Law.

20.2 Publications, documents, specifications, legislation, regulations, standards and the like referenced in this Certificate are those that were current and/or deemed relevant by the BBA at the date of issue or reissue of this Certificate.

20.3 This Certificate will remain valid for an unlimited period provided that the product/system and its manufacture and/or fabrication, including all related and relevant parts and processes thereof:

- are maintained at or above the levels which have been assessed and found to be satisfactory by the BBA
- continue to be checked as and when deemed appropriate by the BBA under arrangements that it will determine
- are reviewed by the BBA as and when it considers appropriate.

20.4 The BBA has used due skill, care and diligence in preparing this Certificate, but no warranty is provided.

20.5 In issuing this Certificate the BBA is not responsible and is excluded from any liability to any company, firm, organisation or person, for any matters arising directly or indirectly from:

- the presence or absence of any patent, intellectual property or similar rights subsisting in the product/system or any other product/system
- the right of the Certificate holder to manufacture, supply, install, maintain or market the product/system
- actual installations of the product/system, including their nature, design, methods, performance, workmanship and maintenance
- any works and constructions in which the product/system is installed, including their nature, design, methods, performance, workmanship and maintenance
- any loss or damage, including personal injury, howsoever caused by the product/system, including its manufacture, supply, installation, use, maintenance and removal
- any claims by the manufacturer relating to CE marking.

20.6 Any information relating to the manufacture, supply, installation, use, maintenance and removal of this product/system which is contained or referred to in this Certificate is the minimum required to be met when the product/system is manufactured, supplied, installed, used, maintained and removed. It does not purport in any way to restate the requirements of the Health and Safety at Work etc. Act 1974, or of any other statutory, common law or other duty which may exist at the date of issue or reissue of this Certificate; nor is conformity with such information to be taken as satisfying the requirements of the 1974 Act or of any statutory, common law or other duty of care.